

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 312 623 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

21.05.2003 Bulletin 2003/21

(51) Int Cl.⁷: **C08F 210/06, F16L 9/12**

(21) Application number: **01127005.5**

(22) Date of filing: **14.11.2001**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

Designated Extension States:

AL LT LV MK RO SI

(71) Applicant: **Borealis Technology Oy**
06101 Porvoo (FI)

(72) Inventor: **The designation of the inventor has not
yet been filed**

(74) Representative: **VA TECH Patente GmbH & Co**
Penzinger Strasse 76
1141 Wien (AT)

(54) **Pressure pipes**

(57) The invention relates to a pressure pipe with increased long-term pressure resistance which is comprised of a polypropylene composition. The polypropylene composition is comprised of a polypropylene copolymer which is at least partially crystallised in the β -modification.

EP 1 312 623 A1

Description**Field of the invention**

- 5 [0001] The invention relates to a pressure pipe with increased long-term pressure resistance which is comprised of a polypropylene composition.

Background of the invention

- 10 [0002] Polymer materials are frequently used for pipes for various purposes, such as fluid transport, i.e. transport of liquid or gas, e.g. water or natural gas, during which the fluid can be pressurized. Moreover, the transported fluid may have varying temperatures, usually within the temperature range of about 0 °C to about 70 °C. Such pipes are preferably made of polyolefins, usually polyethylene or polypropylene.
- 15 [0003] Because of the high temperatures involved, hot water pipes of polymer materials represent a particularly problematic type of polymer pipe. Not only must a hot water polymer pipe fulfill the requirements necessary for other ordinary polymer pipes, such as cold water pipes, but in addition it must withstand the strain associated with hot water. The temperatures of the hot water in a hot water pipe, typically used for plumbing and heating purposes, range from 30-70 °C which means that the pipe must be able to withstand a higher temperature than that for a secure long term use. Peak temperatures may be as high as 100 °C.
- 20 [0004] According to the draft standard prEN 12202 a hot water polypropylene pipe must meet the requirement of at least 1000 h before failure at 95 °C and 3.5 MPa pressure if it is a random copolymer.
- [0005] The Austrian patent AT 404 294 B discloses a pressure pipe which consists of a homopolymer of polypropylene which consists predominantly of the hexagonal β -form of polypropylene with a nucleating agent which is based on an amide. These pipes have an increased resistance to rapid crack propagation.
- 25 [0006] The published Japanese patent application JP 05-170932 discloses polypropylene pipes for watersupply purposes. It is disclosed, that by adding certain anti-oxidants to different kinds of polypropylene, the endurance time of these pipes can be increased.
- None of these documents discloses polypropylene pipes with an increased long-term pressure resistance.

30 **Object of the Invention**

- [0007] It is therefore the object of the present invention to provide pressure pipes with an increased long-term pressure resistance which are comprised of a polypropylene composition.
- 35 [0008] This object has been solved by a polypropylene composition which is comprised of a propylene copolymer which comprises
- 73.0 - 99.0 wt% of propylene and
- 1 to 20 wt% of one or more C₄-C₈ α -olefins and/or up to 7 wt% of ethylene,
- where the propylene copolymer is at least partially crystallized in the β -modification.
- 40 [0009] **Long-term pressure resistance** herein means a late occurrence of a knee-point when the pipe is tested according to ISO 1167:1996(E). **Late** means, that the occurrence of a knee-point is shifted to a considerably higher failure time as for conventional polypropylene pipes. A late occurrence of a knee-point also usually encompasses that the slope of a regression line connecting the ductile failure points, in a log-log diagram, is flatter than compared with present art.

45 **Descriptions of ductile failure, brittle failure and knee-point (at a given temperature):**

- [0010] A ductile failure is defined as a macroscopically visible deformation of the pipe geometry, e.g. a ruptured bubble. A brittle failure or a weeping failure, which both are in the following referred to as non-ductile (n.d.), is defined as a failure which does not result in a visible deformation of the pipe geometry, e.g. cracks, fissures. A weeping failure typically has such a small crack, that it needs to be visually inspected to see water penetrating out of the pipe wall. Brittle failures are detected by pressure loss in the pipe pressurising equipment. A knee-point at a given temperature is defined as the intersection of the regression line representing the ductile failures and the regression line representing the non-ductile failures.
- In order to calculate the lifetime of a pipe at longer times, pipes need to be pressure tested at different temperatures according to ISO 1167. Pressure test results at higher temperatures, e.g. at 110 °C or 95 °C, allow to extrapolate the life time of the pipe to lower temperatures. The extrapolation procedure is described in detail in the ISO TR 9080 (1992) standard, commonly referred to as the standard extrapolation method (SEM). This calculation method, which was defined for plastics pipes, fits a regression line in all the ductile breaks for a given test temperature and a second regression
- 55

line in the non-ductile breaks of this given temperature. The non-ductile lines are always steeper than the ductile lines. The calculation method is based on the combination of the set of failure data, where at a given temperature pipes are tested at different stress levels to get different failure times. Also pipes which are still "in progress", i.e. no pipe failure has been observed and the time under test at a given time and stress is known, may also be added to the set of data.

5 This is particularly valid for pipes still under test at longer test times. Extrapolation time limits are also defined in this standard, e.g. when test results are available at 95 °C up to one year, these test results are allowed to be extrapolated to 55 °C (i.e. 95 minus 40) at 50 years. 50 years of extrapolation are relevant for building pipes, but also shorter times such as 10 to 20 years of extrapolation are relevant, e.g. for pipes for industrial use.

10 The slopes of the lines of the non-ductile failures are steeper (i.e. more negative) than that of the ductile failures (when the same log(failure time) vs. log(hoop stress) diagram is used as given in Fig. 1). Since the point where the knee-point occurs, greatly influences the extrapolated stress at a given temperature, typically chosen between 30 to 70 °C, with extrapolated lifetimes from 10 to 50 years, it is desirable for the knee-point to be at long times. The claim of the invention is that the knee-point at a given temperature of the new product is shifted to longer times compared to present art.

15 It is also possible, when testing a pipe at a higher temperature such as 95 °C, that a knee-point is not observed within an investigation time of 1 year, which is in fact a particularly preferred behaviour. In such a case it is possible to use only ductile failures for extrapolation of longer times.

20 The slope of the regression line of the ductile failure points has a large influence on the extrapolated life times. It is therefore desirable for this slope for a given temperature to be as large as possible, i.e. the regression line shall be as "flat" as possible ("large", because in the display format of Fig. 1 the slopes are negative values). It is part of the present invention, that the extrapolation line linking the ductile failure points for a given temperature is flatter than present art.

[0011] It has surprisingly been found that pressure pipes which are comprised of the above composition exhibit a remarkably improved behaviour where long-term pressure resistance is concerned.

25 **[0012]** The polypropylene composition of this invention is a composition of a copolymer of propylene with ethylene and/or an α -olefin.

This polypropylene copolymer is a copolymer which contains 73.0 to 99.0 wt%, preferably 83.0 - 99.0 wt%, more preferably 85.5 - 97.0 wt% of propylene and 1 to 20 wt%, preferably 1.0 - 12.0 wt%, more preferably 3.0 - 10.0 wt% of one or more C_4 - C_8 α -olefins and/or up to 7.0 wt%, preferably up to 5.0 wt% and more preferably up to 4.5 wt% of ethylene.

30 **[0013]** The C_4 - C_8 α -olefin is preferably selected from 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene and 1-octene. Particularly preferred is 1-butene

[0014] The polymerisation process for the production of the polypropylene copolymer may be a continuous process or a batch process, utilizing known methods and operating in liquid phase, optionally in the presence of an inert diluent, or in gas phase, or by mixed liquid-gas techniques. The process is preferably carried out in the presence of a stereospecific Ziegler-Natta- or metallocene-catalyst system. The copolymer includes polypropylene copolymers with a monomodal as well as polypropylene copolymers with a bimodal or multimodal molecular weight distribution.

35 **[0015]** The "modality" of a polymer refers to the shape of its molecular weight distribution curve, i.e. the appearance of the graph of the polymer weight fraction as function of its molecular weight. If the polymer is produced in a sequential step process, utilizing reactors coupled in series and using different conditions in each reactor, the different fractions produced in the different reactors will each have their own molecular weight distribution. When the molecular weight distribution curves from these fractions are superimposed into the molecular weight distribution curve for the total resulting polymer product, that curve will show two or more maxima or at least be distinctly broadened in comparison with the curves for the individual fractions. The molecular weight distribution of such a polymer product, produced in two or more serial steps, is called bimodal or multimodal, depending on the number of steps.

40 **[0016]** According to a further embodiment the pipe is comprised of a propylene copolymer which is comprised of 83.0 - 99.0 wt% of propylene and

1 to 12 wt% of one or more C_4 - C_8 α -olefins and/or up to 5.0 wt% of ethylene.

Pipes from these polypropylene compositions exhibit still better long-term pressure resistances.

50 **[0017]** According to the present invention the polypropylene composition has an MFR of 0.1 to 10 g/10 min at 230 °C/2.16 kg. Preferred MFR values 0.1 to 5, more preferably 0.1 to 2, and most preferably MFR values below 1 g/10 min at 230 °C/2.16 kg.

[0018] According to a still further embodiment of the present invention the propylene copolymer is a random polymer.

55 **[0019]** It is advantageous for the pipes according to the invention when the amount of β -crystallinity of the polypropylene copolymer (determined by DSC using the second heat) is at least 50 %, preferably at least 60 %, more preferably at least 70 % and most preferably at least 80 %.

[0020] According to an advantageous embodiment the propylene copolymer comprises a β -nucleating agent, of which any one or mixtures of a mixed crystal of 5,12-dihydroquino(2,3-b)acridine-7,14-dione with quino(2,3-b)acridine-

6,7,13,14(5H, 12H)-tetrone, N,N'-dicyclohexyl-2,6-naphtalen dicarboxamide and salts of dicarboxylic acids with at least 7 carbon atoms with metals of group II of the periodic table are preferred.

[0021] A preferred composition is comprised of a propylene copolymer which is comprised of
 89.0 - 96.0 wt% of propylene and
 3 to 10 wt% of butene and up to
 1.0 wt% of ethylene.

[0022] It is a further object of the present invention to provide a novel way of producing polypropylene pressure pipes with a reduced sensitivity of the measured failure times to the applied hoop stress.

[0023] The above object is achieved by using a polypropylene composition comprised of a propylene copolymer which comprises

73.0 - 99.0 wt% of propylene and

1 to 20 wt% of one or more C₄-C₈ α-olefins and/or up to 7 wt% of ethylene,

where the propylene copolymer is at least partially crystallized in the β-modification, for the production of pressure pipes whose failure time vs. hoop stress relation at 95 °C before a knee-point fits the following type of equation:

$$\text{LOG (hoop stress)} = (\text{slope}) * \text{LOG (failure time)} + (\text{constant}),$$

where (slope) 2 - 0.0300 when the failure is ductile and where the testing is performed according to ISO 1167:1996(E).

[0024] All known polypropylene pipes which are state of the art exhibit a remarkably steeper slope, i.e. more negative (slope)-values, in the region of ductile failure when they are tested according to the above conditions.

In the above equation the item (constant) is dependent upon the chemical composition of the tested polymer, e.g. whether it is a homo- or copolymer. The value of (constant) alone does not give any indication about the pressure resistance properties of a pipe.

[0025] It is a still further object of the present invention to provide polypropylene pressure pipes with an increased long-term pressure resistance, i.e. a delayed occurrence of a knee-point in their failure time vs. hoop stress relation.

[0026] The above object is solved by using a polypropylene composition comprised of a propylene copolymer which comprises

73.0 - 99.0 wt% of propylene and

1 to 20 wt% of one or more C₄-C₈ α-olefins and/or up to 7 wt% of ethylene,

where the propylene copolymer is at least partially crystallized in the β-modification, for the production of pressure pipes whose failure time vs. hoop stress relation at 95 °C before a knee-point fits the following type of equation:

$$\text{LOG (hoop stress)} = (\text{slope}) * \text{LOG (failure time)} + (\text{constant})$$

and where a knee-point does not occur before 1500 hrs of testing according to ISO 1167:1996(E).

[0027] All known polypropylene random copolymer pipes which are state of the art have a knee-point of no longer than 1500 hrs, when pressure testing at 95 °C according to ISO 1167:1996(E). At the date of filing this application (November 2001) only ductile failures and no non-ductile failures have been observed at 95 °C and 70 °C with pipes according to the invention, with some pipes having already been tested for more than 10.000 hrs. Consequently, no knee-point has been observed.

[0028] According to an embodiment of the present invention the propylene copolymer comprises

90.0 - 94.0 wt% of propylene and

6 to 10 wt% of 1-butene,

where (slope) ≥ -0.0250.

[0029] Pressure pipes from the above compositions of propylene/1-butene copolymers have a very flat slope in their ductile failure region.

[0030] According to a further embodiment of the present invention the propylene copolymer comprises

89.4 - 95.9 wt% of propylene and

4 to 10 wt% of 1-butene and

0.1 to 0.6 wt% of ethylene,

where (slope) ≥ -0.0250.

Pressure pipes from compositions comprising terpolymers of propylene, 1-butene and small amounts of ethylene also have very favourable flat slopes in their ductile failure region.

[0031] According to a still further embodiment of the present invention the propylene copolymer comprises

95 - 97 wt% of propylene and

3 to 5 wt% of ethylene

where (slope) ≥ -0.0220 .

Pressure pipes from the above compositions comprising propylene/ethylene copolymers also have very favourable flat slopes in their ductile failure region.

5 Definition of β -nucleating agent

[0032] As β -nucleating agent any nucleating agent can be used which is suitable for inducing crystallization of polypropylene homo- and copolymers in the hexagonal or pseudohexagonal modification. Mixtures of such nucleating agents may also be employed.

[0033] Suitable types of β -nucleating agents are

- dicarboxylic acid derivative type diamide compounds from C₅-C₈-cycloalkyl monoamines or C₆-C₁₂-aromatic monoamines and C₅-C₈-aliphatic, C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic dicarboxylic acids, e.g.
 - 15 • N,N'-di-C₅-C₈-cycloalkyl-2,6-naphthalene dicarboxamide compounds such as N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide and N,N'-dicyclooctyl-2,6-naphthalene dicarboxamide,
 - N,N'-di-C₅-C₈-cycloalkyl-4,4-biphenyldicarboxamide compounds such as N,N'-dicyclohexyl-4,4-biphenyldicarboxamide and
 - 20 N,N'-dicyclopentyl-4,4-biphenyldicarboxamide,
 - N,N'-di-C₅-C₈-cycloalkyl-terephthalamide compounds such as N,N'-dicyclohexylterephthalamide and N,N'-dicyclopentylterephthalamide,
 - N,N'-di-C₅-C₈-cycloalkyl-1,4-cyclohexanedicarboxamide compounds such as N,N'-dicyclohexyl-1,4-cyclohexanedicarboxamide and
 - 25 N,N'-dicyclohexyl-1,4-cyclopentanedicarboxamide,
- diamine derivative type diamide compounds from C₅-C₈-cycloalkyl monocarboxylic acids or C₆-C₁₂-aromatic monocarboxylic acids and C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic diamines, e.g.
 - 30 • N,N'-C₆-C₁₂-arylene-bis-benzamide compounds such as N,N'-p-phenylene-bis-benzamide and N,N'-1,5-naphthalene-bis-benzamide,
 - N,N'-C₅-C₈-cycloalkyl-bis-benzamide compounds such as N,N'-1,4-cyclopentane-bis-benzamide and N,N'-1,4-cyclohexane-bis-benzamide,
 - N,N'-p-C₆-C₁₂-arylene-bis-C₅-C₈-cycloalkylcarboxamide compounds such as
 - 35 N,N'-1,5-naphthalene-bis-cyclohexanecarboxamide and N,N'-1,4-phenylene-bis-cyclohexanecarboxamide, and
 - N,N'-C₅-C₈-cycloalkyl-bis-cyclohexanecarboxamide compounds such as N,N'-1,4-cyclopentane-bis-cyclohexanecarboxamide and
 - 40 N,N'-1,4-cyclohexane-bis-cyclohexanecarboxamide,
- amino acid derivative type diamide compounds from amidation reaction of C₅-C₈-alkyl, C₅-C₈-cycloalkyl- or C₆-C₁₂-arylamino acids, C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic monocarboxylic acid chlorides and C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic mono-amines, e.g.
 - 45 • N-phenyl-5-(N-benzoylamino)pentaneamide and N-cyclohexyl-4-(N-cyclohexyl-carbonylamino)benzamide.

[0034] Further suitable β -nucleating agents are


- 50 • quinacridone type compounds, e.g. quinacridone, dimethylquinacridone and dimethoxyquinacridone,
- quinacridonequinone type compounds, e.g. quinacridonequinone, a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)-tetrone and dimethoxyquinacridonequinone and
- 55 • dihydroquinacridone type compounds, e.g. dihydroquinacridone, dimethoxydihydroquinacridone and dibenzodihydroquinacridone.

[0035] Still further suitable β -nucleating agents are

- dicarboxylic acid salts of metals from group IIa of periodic system, e.g. pimelic acid calcium salt and suberic acid calcium salt; and
- mixtures of dicarboxylic acids and salts of metals from group IIa of periodic system.

[0036] Still further suitable β -nucleating agents are

- salts of metals from group IIa of periodic system and imido acids of the formula



wherein $x = 1$ to 4 ; $\text{R} = \text{H}$, $-\text{COOH}$, $\text{C}_1\text{-C}_{12}$ -alkyl, $\text{C}_5\text{-C}_8$ -cycloalkyl or $\text{C}_6\text{-C}_{12}$ -aryl, and $\text{Y} = \text{C}_1\text{-C}_{12}$ -alkyl, $\text{C}_5\text{-C}_8$ -cycloalkyl or $\text{C}_6\text{-C}_{12}$ -aryl - substituted bivalent $\text{C}_6\text{-C}_{12}$ -aromatic residues, e.g.

calcium salts of phthaloylglycine, hexahydrophthaloylglycine, N-phthaloylalanine and/or N-4-methylphthaloylglycine.
[0037] Preferred β -nucleating agents are any one or mixtures of N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide, the β -nucleating agents of EP 170889 and those of EP 682066.

[0038] The propylene copolymer which is at least partly crystallized in the β -modification is preferably produced by melt mixing the propylene copolymer base resin with 0.0001 to 2.0 wt% based on the propylene copolymer used, of β -nucleating agents at temperatures from 175 to 250 °C and cooling and crystallizing the melt according to procedures which are state of the art.

Definition of pipe

[0039] The term "pipe" as used herein is meant to encompass pipes in the narrower sense, as well as supplementary parts like fittings, valves and all parts which are commonly necessary for e.g. a hot water piping system.

Pipes according to the invention also encompass single and multilayer pipes, where for example one or more of the layers is a metal layer and which may include an adhesive layer. Other constructions of pipes, e.g. corrugated pipes, are possible as well.

[0040] The propylene compositions used for pipes according to the invention may contain usual auxiliary materials, e.g. up to 40 wt% fillers and/or 0.01 to 2.5 wt% stabilizers and/or 0.01 to 1 wt% processing aids and/or 0.1 to 1 wt% antistatic agents and/or 0.2 to 3 wt% pigments and/or reinforcing agents, e.g. glass fibres, in each case based on the propylene composition used.

For the present invention coloration of the propylene composition is largely irrelevant, however certain pigments, e.g. pigments which are highly active α -nucleating agents, cannot be utilised.

Production of the Pipes

[0041] Pipes according to the invention were produced by first plasticizing the propylene polymer in an extruder at temperatures in the range of from 200 to 250 °C and then extruding it through an annular die and cooling it.

[0042] The extruders for producing the pipes can be single screw extruders with an L/D of 20 to 40 or twin screw extruders or extruder cascades of homogenizing extruders (single screw or twin screw). Optionally, a melt pump and/or a static mixer can be used additionally between the extruder and the ring die head. Ring shaped dies with diameters ranging from approximately 16 to 2000 mm and even greater are possible.

[0043] The melt arriving from the extruder is first distributed over an annular cross-section via conically arranged holes and then fed to the core/die combination via a coil distributor or screen. If necessary, restrictor rings or other structural elements for ensuring uniform melt flow may additionally be installed before the die outlet.

[0044] After leaving the annular die, the pipe is taken off over a calibrating mandrel, usually accompanied by cooling of the pipe by air cooling and/or water cooling, optionally also with inner water cooling.

Experimental part - preparation of the polymer compositions

Base resin I

[0045] The **Propene-1-butene-copolymer** was polymerized in a continuous working polymerization system by using propene, 1-butene, the catalyst compound C and cocatalysts (Triethylaluminium (TEAL), Electron donor (**CMDMS**)).

Catalyst compound C

[0046] As catalyst compound C a commercial available Ziegler/Natta-catalyst (Titaniumchloride catalyst supported on MgCl_2), suitable for the production of polypropylene-copolymers in a monomer suspension is used.

Polymerization

[0047] The polymerization is performed continuously in a prepolymerization reactor and a main polymerization reactor. Temperatures, pressures, catalyst-, monomer- and hydrogen feed in the separate polymerization steps as well as the polymer concentration in the main reactor are kept constant. The molar mass of the copolymer is controlled by adding hydrogen gas. The concentration of hydrogen in the mixture of liquid monomers is continuously measured by gas chromatography. The relevant processing parameters and the analytical results of the resulting polymer are listed in table 1.

[0048] The first polymerization step is performed in a small reactor (equipped with stirrer and cooling system), where an excess of a liquid mixture of the monomers propene and 1-butene is prepolymerized for 9 minutes at 20 °C. Therefore catalyst compound C, mixed with the cocatalyst compounds Triethylaluminium (TEAl) and Cyclohexyl-methyl-dimethoxysilane (CMDMS) as external electron donor, are continuously poured into the prepolymerization unit.

[0049] The prepolymer (product A) is continuously removed from the prepolymerization unit and passed over into the main reactor system (equipped with stirrer and cooling system), where under excess of a liquid mixture of the monomers propene and 1-butene, the final copolymer (B) is formed. Further a mixture of monomers (propene/1-butene) and hydrogen (for molar mass control) are continuously fed into the main reactor. The polymer concentration is kept constant at 517 g/l. A part of the reactor content (polymer- / monomer excess) is continuously removed from the reactor into a degassing unit to separate the formed copolymer (B) from unreacted monomer mixture by evaporation.

[0050] The separated copolymer (B), Base resin I was subjected to a steam treatment, to remove the unreacted monomers and volatile substances, and then dried.

Base resin II

[0051] The **Propene-1-butene-copolymer** was polymerized in a continuous working polymerization system by using propene, 1-butene, the catalyst compound F and cocatalysts (Triethylaluminium (TEAl), Electron donor (DCPDMS)).

Catalyst compound F

[0052] As catalyst compound F a commercial available Ziegler/Natta-catalyst (Titaniumchloride catalyst supported on MgCl_2), suitable for the production of polypropylene-copolymers in a monomer suspension is used.

Polymerization

[0053] The polymerization is performed continuously in a prepolymerization reactor and a main polymerization reactor. Temperatures, pressures, catalyst-, monomer- and hydrogen feed in the separate polymerization steps as well as the polymer concentration in the main reactor are kept constant. The molar mass of the copolymer is controlled by adding hydrogen gas. The concentration of hydrogen in the mixture of liquid monomers is continuously measured by gas chromatography. The relevant processing parameters and the analytical results of the resulting polymer are listed in table 1.

[0054] The first polymerization step is performed in a small reactor (equipped with stirrer and cooling system), where an excess of propene and 1-butene is prepolymerized for 9 minutes at 20 °C. Catalyst compound F, mixed with the cocatalyst compounds Triethylaluminium (TEAl) and Dicyclopentyl-dimethoxysilan (DCPDMS) as external electron donor, are continuously poured into the prepolymerization unit.

[0055] The prepolymer (product D) is continuously removed from the prepolymerization unit and passed over into the main reactor system (equipped with stirrer and cooling system), where under excess of a liquid mixture of the monomers propene and 1-butene, the final copolymer (E) is formed. Further a mixture of monomers (propene/ethene) and hydrogen (for molar mass control) are continuously fed into the main reactor. The polymer concentration is kept constant at 513 g/l. A part of the reactor content (polymer- / monomer excess) is continuously removed from the reactor into a degassing unit to separate the formed copolymer (E) from unreacted monomer mixture by evaporation.

[0056] The separated copolymer (E), Base resin II was subjected to a steam treatment, to remove the unreacted monomers and volatile substances, and then dried

Base resin III

[0057] The **Propene-ethene-1-butene-terpolymer** was polymerized in a continuous working polymerization system by using propene, ethene, 1-butene, the catalyst compound J and cocatalysts (Triethylaluminium (TEAl), Electron donor (CMDMS)).

Catalyst compound J

[0058] As catalyst compound J a commercial available Ziegler/Natta-catalyst (Titaniumchloride catalyst supported on $MgCl_2$), suitable for the production of polypropylene terpolymers in a monomer suspension is used.

Polymerization

[0059] The polymerization is performed continuously in a prepolymerization reactor and a main polymerization reactor. Temperatures, pressures, catalyst-, monomer- and hydrogen feed in the separate polymerization steps as well as the polymer concentration in the main reactor are kept constant. The molar mass of the terpolymer is controlled by adding hydrogen gas. The concentration of hydrogen in the mixture of liquid monomers is continuously measured by gas chromatography. The relevant processing parameters and the analytical results of the resulting polymer are listed in tables 1 and 2.

[0060] The first polymerization step is performed in a small reactor (equipped with stirrer and cooling system), where an excess of a liquid mixture of the monomers propene and 1-butene is prepolymerized for 9 minutes at 20 °C. Therefore catalyst compound J mixed with the cocatalyst compounds Triethylaluminium (TEAl) and Cyclohexyl-methyl-dimethoxysilane (CMDMS) as external electron donor, are continuously poured into the prepolymerization unit.

[0061] The prepolymer (product K) is continuously removed from the prepolymerization unit and passed over into the main reactor system (equipped with stirrer and cooling system), where under excess of a liquid mixture of the monomers propene and 1-butene, under addition of ethene, the final terpolymer (L) is formed. Further a mixture of monomers (propene/1-butene/ethene) and hydrogen (for molar mass control) are continuously fed into the main reactor. The polymer concentration is kept constant at 542 g/l. A part of the reactor content (polymer- / monomer excess) continuously is removed from the reactor into a degassing unit to separate the formed terpolymer (L) from unreacted monomer mixture by evaporation.

[0062] The separated terpolymer (L), Base resin III, was subjected to a steam treatment, to remove the unreacted monomers and volatile substances, and then dried.

Table 1		Base resins		
Parameter	unit	I	II	III
Catalyst system and concentration				
TEAL/CMDMS	g/g	4.85	-	4.85
TEAl/DCPDMS	g/g	-	4.85	-
TEAl/Ti	g/g	218	315	317
TEAl/Ti	mol/mol	91	132	133
Prepolymerization reactor / Liquid monomer phase				
Catalyst compound	-	C	F	J
Feed catalyst compound	g/h	4.04	2.78	3.18
Pressure	bar	34	34	34
Temperature	°C	20	20	20
mean residence time	min	9	9	9
Main reactor / Liquid monomer phase				
Pressure	bar	34	34	34
Temperature	°C	65	65	65
Average residence time catalyst	min	1.48	1.46	1.50

(continued)

Main reactor / Liquid monomer phase				
Polymer concentration in reactor (stationary)	g/l	517	513	542
Feed propylen/1-butene mixture	kg/h	130	130	134
Butene content in monomer feed	Vol%	12.5	13.0	22.0
Ethylene feed	kg/h	-	-	0.8
H ₂ -concentration based on monomer feed	ppm	95	210	110
Polymer production rate final product	kg/h	41.0	30.0	49.5
Final product	-	B	E	K
Analytical results				
MFR (230°/2.16 kp)	g/10 min	0.27	0.41	0.32
Ethylene content in copolymer	wt%	0	0	0.6
Butene content in copolymer	wt%	6.2	6.6	6.1
Xylene cold solubles	wt-%	3.8	2.7	4.1
Melting temperature	°C	145	142	142

Example 1 (Invention):

[0063] The Propene-1-butene-copolymer powder (Base resin I) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and 2 % Masterbatch A and pelletized in a conventional compounding line.

Example 2 (Invention):

[0064] The Propene-1-butene-copolymer powder (Base resin II) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and 2 % Masterbatch A and pelletized in a conventional compounding line.

Example 3 (Invention):

[0065] The Propene-ethene-1-butene-terpolymer powder (Base resin III) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and 2 % Masterbatch A and pelletized in a conventional compounding line.

Example 4 (Invention):

[0066] The Propene-ethene-1-butene-terpolymer powder (Base resin III) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and 0.1 % Calciumpimelate and pelletized in a conventional compounding line.

Example 5 (Invention):

[0067] The commercially available Propene-ethene-copolymer *Borealis RA130E* was mixed with 0.5 % Dioctadecyl 3,3'-thiodipropionate and 2 % Masterbatch A and pelletized in a conventional compounding line.

Comparative example 1:

[0068] The Propene-1-butene-copolymer powder (Base resin I) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and pelletized in a conventional compounding line.

Comparative example 2:

[0069] The Propene-1-butene-copolymer powder (Base resin II) was mixed with 0.07% Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and pelletized in a conventional compounding line.

Comparative example 3:

[0070] The Propene-ethene-1-butene-terpolymer powder (Base resin III) was mixed with 0.07 % Calciumstearate, 0.25 % Pentaerythritol-tetrakis(3,5-di-tert-butyl-4-hydroxyphenyl)propionate, 0.1 % Tris(2,4-ditert-butylphenyl)phosphite, 0.25 % 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol and pelletized in a conventional compounding line.

Comparative example 4:

[0071] As comparative example 4 a commercially available propene-ethene-copolymer grade (*Borealis RA130E*) was used.

Comparative example 5:

[0072] As comparative example 5 a commercial available propene-homopolymer grade (*Borealis BE60-7032*) was used.

Masterbatch A

[0073] Masterbatch A is a commercially available product based on polypropylene and containing the quinacridone pigment "Chinquasia gold" as β -nucleating agent.

Composition of Masterbatch A:

[0074]

49.75 %	Polypropylene
0.25 %	Quinacridone Pigment Orange 48
2 %	Carbon Black Pigment Black 7
4 %	Cr/Sb/Ti oxide Pigment Brown 24
1 %	Chromium oxide Pigment Green 17
1 %	Ni/Sb/Ti oxide Pigment Yellow 53
42 %	TiO ₂ Pigment White 6

Calciumpimelate

[0075] 1 Mol of pimelic acid was reacted with 1 mol calciumcarbonate in a mixture of ethanol and water at 60 - 80 °C. The produced calciumpimelate was filtered and dried.

Description of measurement methods**Determination of β -crystallinity**

5 [0076] The β -crystallinity was determined by Differential Scanning Calorimetry (DSC). DSC was run according to ISO 3146 / part 3 / method C2 with a scan rate of 10 °C/min. The amount of β -modification was calculated from the second heat by the following formula:

$$10 \quad \beta\text{-area} / (\alpha\text{-area} + \beta\text{-area})$$

Since the thermodynamical instable β -modification starts to be changed into the more stable α -modification at temperatures above 150 °C, a part of the β -modification is transferred within the heating process of DSC-measurement. Therefore the amount of β -PP determined by DSC is lower as when measured according to the method of Turner-Jones by WAXS (A. Turner-Jones et. al., Makromol. Chem 75 (1964) 134).

15 "Second heat" means, that the sample is heated according to ISO 3146 / part 3 / method C2 for a first time and then cooled to room temperature at a rate of 20 °C/min. The sample is then heated a second time, also according to ISO 3146 / part 3 / method C2. This second heat is relevant for measurement and calculation.

20 During the "first heat" all thermal history of the sample giving rise to different crystalline structure, which typically comes from different processing conditions and/or methods, is destroyed. Using the second heat for determination of β -crystallinity, it is possible to compare samples regardless of the way the samples were originally manufactured.

XCS

25 [0077] Xylene solubles were determined at 23 °C according to ISO 6427. Xylene solubles are defined as the percent by weight that stays in solution after the polymer sample is dissolved in hot xylene and the solution is allowed to cool to 23 °C.

MFR

30 [0078] The melt flow rates were measured with a load of 2.16 kg at 230 °C. The melt flow rate is that quantity of polymer in grams which the test apparatus standardized to DIN 53 735 extrudes within 10 minutes at a temperature of 230 °C under a weight of 2.16 kg.

Flexural test

[0079] The flexural test was carried out according to the method of ISO 178 by using injection molded test specimens as described in EN ISO 1873-2 (80 x 10 x 4 mm).

Charpy impact strength

[0080] The notched charpy impact strength was carried out according to ISO 179 / 1eA at 23 °C by using injection molded test specimens as described in EN ISO 1873-2 (80 x 10 x 4 mm)

Hoop stress test

45 [0081] Hoop stress tests are performed according to ISO 1167:1996(E). For a better comparability and also for practical reasons (availability of data) only the data at 95 °C are used in this application.

50

55

Table 2

Data of basic polymer													
Base resin	BE60	RA130E		Base resin I		Base resin II		Base resin III					
Example	CE 5	CE 4	E 5	CE 1	E 1	CE 2	E 2	CE 3	E 3	E 4			
Comment		C2-raco		C4-raco		C4-raco		C2C3C4-raco					
Nucleation	β	α	β	α	β	α	β	α	β	α	β	β	β
β -nucleating agent													
Masterbatch A	ppm	12000		12000		20000		20000		20000		20000	1000
Calcium pimelate	ppm												
Analytical & mechanical results													
MFR	230/2.16	g/10'	0.3	0.19	0.20	0.21	0.25	0.31	0.35	0.33	0.35	0.35	0.35
DSC	Tm	°C	152	143	132	143	135	143	134	140	131	131	133
			168		146		149		148		144		145
	Hm	J/g	90	81	62	80	67	92	69	78	63	63	66
				21		16		12		12		12	
Tc	°C	124	103	109	102	108	98	106	106	99	104	104	105
	(DSC)	%	81		80		84		85		84	84	81
β -nucleation	ethylene 1-butene	wt%		4.2	4.2					0.6	0.6	0.6	0.6
		wt%											
Extraction	XCS	%	2.3	6.9	7.5	3.1	2.1	2.2	2.8	3.2	3.4	3.4	2.9
		+ 23°C	kJ/m ²	85	18	90	12	82	9	74	11	84	84
Flex test	Flex Mod	MPa	1215	828	740	972	959	1051	998	949	902	902	888
Failure times [h] / Failure mode													
hoop stress at 95°C	3.5 MPa	7845 / nD	7663 / nD	6298 / D	13000 ip	13000 ip	4323 / nD	13000 ip	12000 ip	12000 ip	12000 ip	12000 ip	12000 ip
	3.8 MPa	6946 / nD	3020 / nD	59 / D	7185 / nD	5885 / D		10558 / D	6712 / nD	5269 / D	5317 / D	5317 / D	5317 / D
	4.0 MPa	6511 / nD	2264 / nD	7 / D	2855 / nD	248 / D		1301 / D	199 / D	199 / D	204 / D	204 / D	204 / D
	4.2 MPa		1079 / nD		1151 / nD	49 / D	2860 / nD	71 / D	2499 / nD	37 / D	36 / D	36 / D	36 / D
	4.5 MPa	2769 / nD	684 / nD		1151 / nD	6 / D	866 / nD	8 / D	1022 / nD	6 / D	5 / D	5 / D	5 / D
	4.9 MPa		220 / D										
	5.0 MPa	1939 / nD	120 / D										
	5.1 MPa		80 / D										
	5.2 MPa		44 / D										
	5.5 MPa	726 / D											
6.0 MPa	58 / D												

Failure modes:**[0082]**

- 5 D ... ductile failure
 nD ... non-ductile failure
 ip ... testing in progress, no failure until specified time.

10 **[0083]** Comparative examples CE4 and CE5 show both ductile and non-ductile failures at 95 °C. A regression line through the non-ductile failure points, when put into a log/log diagram as explained earlier, is steeper than one through the ductile failure points (for each example), when put into a log/log diagram. Therefore all of the comparative examples CE4 and CE5 display a knee-point. On the other hand, examples E1-E4 according to the invention do not show any non-ductile failure points, all failure points, including the "ip - in progress" pipes lay on a straight line. Testing is under way for more than one year (i.e. 12000 and 13000 hours) and only ductile failure points can be used of extrapolation

15 in order to get the extrapolated life time at 50 °C.
 The longest knee-points at 95 °C for present art are at the following times: CE1 < 1151 h (nD); CE2 < 866 h (nD); CE3 < 1022 h (nD); CE4: between 220 h (D) and 684 h (nD); CE5: between 726 h (D) and 1939 h (nD).

The examples according to the invention (E1 to E4) do not show knee-points at times > 5885 h (D) for E1; > 10558 h (D) for E2; > 5269 h (D) for E3 and > 5217 h (D) for E4 and at times of > 12000 h and > 13000 h all pipes are still in progress. Only one straight line is present for E1 to E4, thus higher stress levels will be achieved when extrapolated to lower temperatures to 10 to 50 years.

20 Comparing the slopes of CE1 to CE5 it is evident that they are steeper than the slopes of E1 to E4 in their ductile region. E3 and E4, two beta-nucleated ethene-propene-butene terpolymers, show, when compared to CE3, a non beta-nucleated terpolymer of the same base resin, that the same phenomena like much prolonged or non-present knee-point and flatter ductile line also hold for ethene-propene-butene terpolymers.

25 E1 and E2, two beta-nucleated propene-butene copolymers, show, when compared to CE1 and CE2, non beta-nucleated propene-butene copolymers of the same base resin, that the same phenomena like much prolonged or non-present knee-point and flatter ductile line also hold for propene-butene copolymers.

30 E5, a beta-nucleated ethene-propene copolymer, show, when compared to CE4, a non beta-nucleated ethene-propene copolymer of the same base resin, that the same phenomena like much prolonged or non-present knee-point and flatter ductile line also hold for ethene-propene copolymers.

[0084] The diagram in Fig. 1 is a log/log representation of comparative examples CE4 and CE5 and of inventive example E2. The lines which are drawn through the data points of CE4 and CE5 are drawn by hand. It is however clearly visible, that for each set of data - with the exception of E2 - a distinctive knee-point is present at the intersection of the respective ductile and non-ductile regression lines. It is also clearly visible that the slopes of the regression lines of CE4 and CE5 in their ductile region is steeper than the slope of the regression line of E2. The number of data points in the non-ductile region of CE4 and CE5 is different from the number of data presented in table 2. This does however not change the time of occurrence of a knee-point or the slope of the regression line in the ductile region.

35 The regression line through the data points of ductile failure of E2 is exactly calculated and the equation of the regression line (which is actually a polynomial regression curve, which appears as a straight line in the double logarithmic representation) is included in Fig. 1. The exponent in the equation is what is referred to herein as (slope).

40 The single data point which is denoted as E2 (i.p.), which means that the pipe is still under testing, is not included in the regression analysis. This data point will slowly continue to move to the right of the diagram as time progresses and it will either be the first non-ductile failure point of this data series (after more than 13000 hours !) or a still further ductile failure point.

Claims

- 50 1. Pressure pipe with increased long-term pressure resistance comprised of a polypropylene composition **characterized in that** the polypropylene composition is comprised of a propylene copolymer which comprises 73.0 - 99.0 wt% of propylene and 1 to 20 wt% of one or more C₄-C₈ α-olefins and/or up to 7.0 wt% of ethylene, where the propylene copolymer is at least partially crystallized in the β-modification.
- 55 2. Pipe according to claim 1, **characterized in that** the propylene copolymer is comprised of 83.0 - 99.0 wt% of propylene and 1 to 12 wt% of one or more C₄-C₈ α-olefins and/or up to 5.0 wt% of ethylene.

3. Pipe according to any one of claims 1-2, **characterized in that** the polypropylene composition has an MFR of 0.1 to 10 g/10 min at 230 °C/2.16 kg.

4. Pipe according to any one of claims 1-3, **characterized in that** the propylene copolymer is a random polymer.

5. Pipe according to any one of claims 1-4, **characterized in that** the amount of β -crystallinity of the polypropylene copolymer (determined by DSC using the second heat) is at least 50 %.

6. Pipe according to any one of claims 1-5 **characterized in that** the propylene copolymer comprises a β -nucleating agent.

7. Pipe according to claim 6 **characterized in that** the β -nucleating agent comprises any one or mixtures of a mixed crystal of 5,12-dihydro-quino(2,3-b)acridine-7,14-dione with quino(2,3-b)acridine-6,7,13,14(5H, 12H)-tetrone, N, N'-dicyclohexyl-2,6-naphtalen dicarboxamide and salts of dicarboxylic acids with at least 7 carbon atoms with metals of group II of the periodic table.

8. Pipe according to any one of claims 1-7, **characterized in that** the propylene copolymer is comprised of 89.0 - 96.0 wt% of propylene and 3 to 10 wt% of butene and up to 1.0 wt% of ethylene.

9. Use of a polypropylene composition comprised of a propylene copolymer which comprises 73.0 - 99.0 wt% of propylene and 1 to 20 wt% of one or more C_4 - C_8 α -olefins and/or up to 7 wt% of ethylene, where the propylene copolymer is at least partially crystallized in the β -modification, for the production of pressure pipes whose failure time vs. hoop stress relation at 95 °C before a knee-point fits the following type of equation:

$$\text{LOG (hoop stress)} = (\text{slope}) * \text{LOG (failure time)} + (\text{constant}),$$

where (slope) 2 - 0.0300 when the failure is ductile and where the testing is performed according to ISO 1167:1996(E).

10. Use of a polypropylene composition comprised of a propylene copolymer which comprises 73.0 - 99.0 wt% of propylene and 1 to 20 wt% of one or more C_4 - C_8 α -olefins and/or up to 7 wt% of ethylene, where the propylene copolymer is at least partially crystallized in the β -modification, for the production of pressure pipes whose failure time vs. hoop stress relation at 95 °C before a knee-point fits the following type of equation:

$$\text{LOG (hoop stress)} = (\text{slope}) * \text{LOG (failure time)} + (\text{constant})$$

and where a knee-point does not occur before 1500 hrs of testing according to ISO 1167:1996(E).

11. Use according to any one of claims 9-10, **characterized in that** the propylene copolymer comprises 90.0 - 94.0 wt% of propylene and 6 to 10 wt% of 1-butene, where **(slope)** \geq -0.0250.

12. Use according to any one of claims 9-11, **characterized in that** the propylene copolymer comprises 89.4 - 95.9 wt% of propylene and 4 to 10 wt% of 1-butene and 0.1 to 0.6 wt% of ethylene where **(slope)** \geq -0.0250.

13. Use according to any one of claims 9-10, **characterized in that** the propylene copolymer comprises 95 - 97 wt% of propylene and 3 to 5 wt% of ethylene

where **(slope)** ≥ -0.0220 .

14. Multi-layer pipe where at least one of the layers is comprised of a pipe according to any one of the claims 1-13.

5

10

15

20

25

30

35


40

45

50

55

Fig. 1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 7005

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D,X	AT 404 294 B (PCD POLYMERE GESELLSCHAFT M.B.H.) 27 October 1998 (1998-10-27) * the whole document *	1-14	C08F210/06 F16L9/12
X	& WO 99 40151 A (PCD POLYMERE GESELLSCHAFT M.B.H.) 12 August 1999 (1999-08-12) * the whole document *	1-14	
X	WO 99 24479 A (BOREALIS AS ;JAEAESKELAEINEN PIRJO (FI); MALM BO (FI); HUOVINEN PA) 20 May 1999 (1999-05-20) * page 6, line 9 - page 20, line 5; claims 34-44; examples *	1-6,9, 10,13,14	
D,A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 582 (C-1123), 22 October 1993 (1993-10-22) -& JP 05 170932 A (MITSUBISHI PETROCHEM CO LTD), 9 July 1993 (1993-07-09) * abstract *	1-14	
A	WO 96 11216 A (BOREALIS AS ;JAEAESKELAEINEN PIRJO (FI); KARBASI AMIR KIUMARS (FI)) 18 April 1996 (1996-04-18) * claims; examples; tables *	1-14	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08F F16L
A	EP 0 791 609 A (HOECHST AG) 27 August 1997 (1997-08-27) * the whole document *	1-14	
A	WO 96 24623 A (SASTECH PTY LTD ;SASOL CHEMICALS EUROP LTD (GB); JOUBERT DAWID JOH) 15 August 1996 (1996-08-15) * page 23, line 6 - line 12; claims; examples; tables *	1-14	
A	DE 33 19 515 A (KABELMETAL ELECTRO GMBH) 29 November 1984 (1984-11-29) * the whole document *	14	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 16 April 2002	Examiner Kaumann, E
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/92 (P/4C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 7005

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-04-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
AT 404294 B	27-10-1998	AT 1697 A	15-02-1998
WO 9924479 A	20-05-1999	AU 1035799 A	31-05-1999
		BR 9814854 A	03-10-2000
		CA 2308075 A1	20-05-1999
		CN 1285851 T	28-02-2001
		EP 1028985 A1	23-08-2000
		WO 9924479 A1	20-05-1999
		JP 2001522904 T	20-11-2001
JP 05170932 A	09-07-1993	NONE	
WO 9611216 A	18-04-1996	AT 198337 T	15-01-2001
		AU 704643 B2	29-04-1999
		AU 3655395 A	02-05-1996
		BR 9509319 A	14-10-1997
		DE 69519742 D1	01-02-2001
		DE 69519742 T2	19-04-2001
		EP 0785954 A1	30-07-1997
		ES 2153497 T3	01-03-2001
		WO 9611216 A1	18-04-1996
		JP 10506952 T	07-07-1998
		US 6300420 B1	09-10-2001
EP 0791609 A	27-08-1997	DE 19606510 A1	28-08-1997
		AU 1472797 A	28-08-1997
		BR 9701045 A	15-12-1998
		CA 2198177 A1	22-08-1997
		CZ 9700542 A3	17-09-1997
		EP 0791609 A2	27-08-1997
		HU 9700490 A2	29-12-1997
		JP 9235328 A	09-09-1997
		NO 970799 A	25-08-1997
		PL 318608 A1	01-09-1997
		SK 23297 A3	07-10-1998
		TR 9700145 A2	21-09-1997
		US 2002010297 A1	24-01-2002
WO 9624623 A	15-08-1996	AU 4544796 A	27-08-1996
		BR 9607415 A	23-06-1998
		CN 1173881 A	18-02-1998
		EP 0808334 A1	26-11-1997
		WO 9624623 A1	15-08-1996
		HU 9802670 A2	29-03-1999
		US 6111047 A	29-08-2000
		ZA 9600626 A	15-08-1996

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 7005

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-04-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 3319515 A	29-11-1984	DE 3319515 A1	29-11-1984

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

PUB-NO: EP001312623A1
DOCUMENT-IDENTIFIER: EP 1312623 A1
TITLE: Pressure pipes
PUBN-DATE: May 21, 2003

ASSIGNEE-INFORMATION:

NAME	COUNTRY
BOREALIS TECH OY	FI

APPL-NO: EP01127005
APPL-DATE: November 14, 2001

PRIORITY-DATA: EP01127005A (November 14, 2001)

INT-CL (IPC): C08F210/06 , F16L009/12

EUR-CL (EPC): C08F210/06 , C08F210/16 ,
F16L009/127

ABSTRACT:

CHG DATE=20030702 STATUS=O>????The invention relates to a pressure pipe with increased long-term pressure resistance which is comprised of a polypropylene composition. The polypropylene composition is comprised of a polypropylene copolymer which is at least partially crystallised in the beta -modification.